

(19)The Korean Intellectual Property Office (KR)  
Unexamined Patent Application (A)

(51) Int.Cl. 6  
E04C 1/00

Application No	KR1981-0004743.
Application Date	1981-12-05
Publication No	KR1983-0007986.
Publication Date	1983-11-09
Agent	Jun-Hang Jeon
Inventor	Jun-Yeong Koh Seong-Ryong Koh
Applicant	Jun-Yeong Koh Seong-Ryong Koh
Examination	Not requested
Title of Invention	The manufacturing method of block and the improved loam brick.



Abstract

Content none.



Description

[Title of invention]

The manufacturing method of block and the improved loam brick.

This content did not gather the technical content since the main part disclosure gun.



Scope of Claims

Claim 1 :

The manufacturing method which after equality-mixes to the amount which becomes the soil curable composition consisting of text, as described above, the silicon oxide of 14-16%, the sulfuric acid of 5-6%, the calcium oxide of 51-53%, the ferric oxide of 5-6%, the aluminium oxide of 10-11%, and the magnesium oxide of 5-6% and remainder (the lignin sulfonic acid salt, the stearate NaOH, and the mixture of tripolyphosphate and silica) of 3-5% with about 3-5% of the cement in the cement, characterizes to uniformly mix to the amount

giving an order with the main raw material hygroscopic coefficient of soil and is decided with the soil and lofty to the publicly known oil-hydraulic press etc. pressurized. Of block and loam brick.

In the above case, percent the mode wt%.

※ list of reference: it discloses with the initial application contents.