

(19)The Korean Intellectual Property Office (KR)
Unexamined Patent Application (A)

(51) Int.Cl. 6
C04B 14/10

Application No	KR1984-0000328.
Application Date	1984-01-26
Publication No	KR1985-0005385.
Publication Date	1985-08-24
Agent	Yun-Bae Kim
Inventor	Seong-Ha Park
Applicant	HANKUKIND CO., LTDSeong-Ha Park
Examination	Requested
Title of Invention	The manufacturing method of the high intensity loam brick.



Abstract

Content none.



Description

[Title of invention]

The manufacturing method of the high intensity loam brick.

This content did not gather the technical content since the main part disclosure gun.



Scope of Claims

Claim 1 :

The method for manufacturing the loam brick of the high intensity characterizing *** as the amount in which the clay is to the main component and in which the cement is added and in which the loam brick is manufactured and coming under the waterproofing hardener consisting of the clay component of about 20-50 mesh size, and the stearic acid, calcium carbonate, calcium chloride, dichromic acid, magnesium chloride, calcium hydroxide, polyvinyl alcohol in *** cement and this mixed material the acidproof cement is mixed to the volume ratio of 9:1.5:1 about the volume of the mixed material to about 30-40%.

※ list of reference: it discloses with the initial application contents.

